

ARMDECKCLEAN

ARMOR RENEW DECK CLEANER



ArmorPoxy Inc.
1260 North Ave
Plainfield, NJ 07062
armorpoxy.com
E: info@armorpoxy.com
P: 888-755-7361

READ ALL INSTRUCTIONS BEFORE BEGINNING PROJECT

APPLICATION

DIRECTIONS - MANUAL APPLICATION

Mix ratio=1:16 (concentrate to water).

For manual application mix 1 cup of concentrate with 1 gallon of water to clean approximately 250 sq. ft. (Less on rougher surfaces). Can be applied by pump up sprayer, brush or roller. Simply apply to surface, leave for 5 to 10 minutes and wash off. For more aggressive mix use 2 cups of concentrate per 1 gallon of water.

DIRECTIONS - PRESSURE WASHER

Contains anti-corrosive agents to safeguard pressure washer parts (bleach erode O-rings).

- Rinse surrounding plants with water, before and after application.
- Wet surface to be cleaned, prior to applying the product.
- Place detergent application siphon tube and screen fitter directly into container. Open meter value (if applicable) for maximum product flow. For reservoir machines, pour product (full strength into pressure washer).
- Spray at low pressure onto a wet surface.
- On vertical surfaces, always spray from the top down.
- Allow product to remain on the surface for 5 to 10 minutes to penetrate. Do not allow product to dry on surface.
- Remove siphon tube from solution and rinse surface with high pressure spray thoroughly.
- Flush siphon tube with clean water prior to storage.

NOTE: ALWAYS MIX WITH WATER WHEN APPLYING TO A HOUSE EXTERIOR.

DIRECTIONS - MILL GLAZE REMOVAL

By using as directed on pressured treated wood you will remove mill glaze and minimize the effects of wax and water repellants that may be present in the new wood. This will greatly improve the adhesion of Renew to wood decking and reduce cure time, allowing coatings to be applied sooner to new pressure treated wood.

- Apply cleaner undiluted, let it stay on the surface 5-10 minutes to penetrate.
- Scrub surface thoroughly with nylon brush to remove mill glaze.
- Rinse the surface clean to remove any residue and allow to dry.
- If the water still beads on the surface, repeat steps 1-3.
- Apply RENEW within 7 days of this process.

IMPORTANT - READ ENTIRE DIRECTION MANUAL BEFORE USING

- When using a pressure treated washer to clean painted surfaces, please be aware that water pressure alone may remove paint, or highlight existing discoloration caused by the sun's UV rays.
- From the garden hose, rinse nearby plants with clean water.
- Always test on an inconspicuous area first.
- Any overspray can be neutralized with large volumes of water.
- Extremely soiled or mildewed surfaces may need to be scrubbed with a bristle brush, and a second application, may be needed. Mildew may not be completely removed from porous surfaces.
- For best results when cleaning decks, apply by pump -up garden sprayer, leave for 5 to 10 minutes, and rinse off with water.
- For heavy oil and grease stains (such as on driveways and garage floors), pour product directly onto stains, Allow to penetrate for 10 minutes, then follow normal application procedures.
- In case of severe oil and grease stains on porous surfaces, oil may bleed to the surface or leave a residual stain. Repeat applications may lighten stains, but not remove completely.
- Do not mix this product with other chemicals.

CLEAN UP

- Use mild soap and water

KEEP FROM FREEZING. CLOSE CONTAINER AFTER EACH USE TO PRESERVE PRODUCT.