

**ARM814RX****MIXING AND APPLICATION INSTRUCTIONS: ArmorRoof Liquid Roof Coating With Granules****STORAGE**

Store product in an area so as to bring the material to normal room temperature before using. Continuous storage should be between 60 and 80 degree F.

**MIXING**

Mix the material before use as needed to provide a uniform mixture. Mix with slow speed equipment to minimize air being whipped into product.

**SURFACE PREPARATION**

Make certain that the substrate where the product is to be applied is clean, sound and free of all laitance, dirt, dust, oil, grease, water, dew or foreign contaminants. Power washing will be an effective preparation method for most substrates. Power washing will be an effective preparation method for most substrates. Wire brush or abrasive blast all loose and scaling rust from metal surfaces. When topcoating EPDM or seamed roofs, make sure all seams are secure. Precautions should be exercised when coating surfaces to determine the compatibility of certain insulation boards such as EPS and the effect that the coating may have on the underlying insulation board. A suitable test patch can be applied to determine suitability. Surface must be dry before application.

**ENVIRONMENTAL CONDITIONS**

Do not apply material when temperature is below 40°F during the application time or drying period. Apply material when RH is below 90% for best results. Allow for adequate dry times between coats and before inclement weather or rain. Higher humidity or lower temperatures will slow the dry time.

**APPLICATION**

First, mask off the area where the liquid rubber walkway is to be installed. Then pour/spread walkway liquid rubber onto masked off area. Next, firmly press down on the material with a PHENOLIC CORE roller and spread the material evenly on the surface. Pour only enough material at one time that allows for rolling the material before it becomes tack free. Firm application pressure applied on the phenolic core roller will provide the texture and assure that the material is not being applied too thick. Be sure to apply this product at the specified coverage rate or recommended mil thickness. Some adhesives on existing structures (used to bond the rubber sheets to the deck/structures) may degrade, or are of a poor quality and may not re-bond when the swelling has recovered. Should this occur, you may need to re-bond the sheet rubber with quality adhesives. As we have no control over the type of adhesives used on existing structures, we cannot be held responsible for such occurrences. Apply one gallon per 17.5 square feet per coat (one coat recommended). Always check the substrate for foreign contamination and water before coating. NOTE: If applying over porous substrates, such as concrete but not limited to only concrete, always apply a test patch to determine suitability concerning out-gassing, which could result in pin-holing in both the first coat and subsequent coats as well as potential blisters from the out-gassing.

**REOPEN SERVICE TIME**

Take notice of the full cure time and do not open the area to abusive use before the full characteristics of the coating is achieved. Apply when weather permits 24 hours of rain free curing.

**MAINTENANCE**

Provide for routine maintenance of your roof to assure years of trouble free performance. Ponded water areas without positive flow of debris to drain where the debris is left to build up and accumulate and cycle through drying cycles can eventually cause the debris to bond to the coating and restrict the natural elongation of the coating. This can cause delaminations and tearing over substrates by preventing the coating from moving (expansion and contraction) with the substrate it is applied over. Accordingly, remove debris or flush the debris to drain as routine maintenance before it can build up and affect the coating.

**NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY**

*We warrant that our products are manufactured to strict quality assurance specifications and that the information supplied by us is accurate to the best of our knowledge. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you shall make your own tests to determine the suitability of our product for your particular purpose. Any use or application other than recommended herein is the sole responsibility of the user. Listed physical properties are typical and should not be construed as specifications. **NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABLE OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT.** We shall have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Our products contain chemicals that may **CAUSE SERIOUS PHYSICAL INJURY. BEFORE USING, READ THE MATERIAL SAFETY DATA SHEET AND FOLLOW ALL PRECAUTIONS TO PREVENT BODILY HARM.***