PRODUCT DESCRIPTION

ARM8000X

ARMOR POXY

ArmorPoxy Inc. 1260 North Ave Plainfield, NJ 07062 armorpoxy.com E: info@armorpoxy.com

P: 888-755-7361

I/O Low Voc Water Based Epoxy

Specially formulated Armorpoxy I/O water-based 2-part epoxy is ideal for use in a variety of areas where traditional epoxies may not be suitable, or a lower cost epoxy is desired. This product comes in two parts. Part A and Part B. Part A is the resin. Part B is the pigmented hardener.

BENEFITS AND PROPERTIES (at 73°F)

- · Pot Life: 60 Minutes
- · Touch Drv: 30 Minutes
- Open To Foot Traffic: 2 Hours, depending on film thickness
- Excellent Adhesion to most metal & polymer roofing
- Low VOC (47 to 49 grams per liter)
- Water Cleanable
- Easy To Apply
- Fills Cracks up to 1/8" Wide
- Low Odor
- · Very Good UV Resistance
- Non-Yellowing

APPLICATION USES

- Brick Driveways
- Asphalt Driveways and parking lots
- Rigid vinyl floor tiles
- Asphalt, bitumen, EPDM and TPO roofing
- Aluminum & sheet metal roofing
- Concrete

APPLICATION METHOD

Roller, Serrated Squeegee, Spray

PACKAGING

- 2.5 Gals Kit (colored)
- 1.5 Gal Kit (clear)

PRECAUTIONS

Wear protective clothing and gloves. This is necessary when working with all epoxies. Read their respective Safety Data Sheets.

LIMITATIONS (Do Not Apply)

- Oil Soaked Surfaces
- Polished or Smooth surfaces
- Concrete with densifiers or hardeners.
- If rain is expected within 3 Hours.
- If temperatures are below 50°F
- **Thick Film Application**

PHYSICAL PROPERTIES

Resin Type Solids by Weight Viscosity (Colored) Water-based epoxy 32% (± 2.0%) Part A: 32 (+/-5 seconds)

#3 Zahn cup @ 77 degrees F

Part B: 42 (+/-5 seconds) #2 Zahn cup @ 77 degrees F.

Weights Per Gallon (Colored)

Part A: 9.44 (±.25) lbs. 10.77 (±.25) lbs. Part B: Parts A & B: 10.52 (±.25) lbs. 47-49 Grams per liter

VOC Ambient Colors Available Gray, Beige, Clear Mix Ratio Colored 4 Parts B to 1 Part A Mix Ratio Clear 3 Parts B to 1 Part A Coverage Per Gallon Appx. 250-300 sq.ft. Coverage may vary

Pot Life (Working Time)

Dry Times Dry To Touch

Open to Foot Traffic/Topcoat Shelf Life

4-6 hours @ 73 F

60 Minutes @ 73 F

24 hours (will vary depending on applied thickness)

One year in unopened container

CLEAN UP/PREPARATION

ARM8000X can be cleaned up with warm, soapy water while wet. Mechanical grinding is necessary once it's cured to remove.

CAUTION

Do not freeze! Keep product stored indoors at room temperature.

All products manufactured by us are warranted to be first class material and free from defects in material and workmanship.

Product is warranted against de lamination for 2 years. It does not apply to de lamination caused by oil, grease, hydro-static pressure or force majeure. De lamination showing coating / asphalt adhesion is not covered.

Liability under this warranty is limited to the net purchase price of any such products proven defective or, at our option, to the repair or replacement of said products upon their return to us transportation prepaid. All claims hereunder on defective products must be made in writing within 30 days after the receipt of such products in your plant and prior to further processing or combining with other materials and products.

THIS WARRANTY IS EXCLUSIVE OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, AND NO REPRESENTATIVE OF ANY OR OURS OTHER PERSON IS AUTHORIZED TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH THE SALE OF OUR PRODUCTS