

INSTRUCTIONS

ARMPOLY85-CM



ArmorPoxy Inc.
1260 North Ave
Plainfield, NJ 07062
armorpoxy.com
E: info@armorpoxy.com
P: 888-755-7361

85% SOLIDS POLYASPARTIC COATING (CLEAR)

PLEASE READ INSTRUCTIONS THOROUGHLY BEFORE APPLICATION BEGINS. THIS IS A FAST DRYING PRODUCT WITH < 15 MINUTES OF WORKING TIME.

PRODUCT STORAGE

Store product at normal room temperature before using. Continuous storage should be between 60 and 90 degrees F.

SURFACE PREPARATION

The most suitable surface preparation would be sand blasting, diamond grinder w/30 grit or coarser or acid etching (followed by a thorough rinsing) to remove all laitance and provide a suitable application profile. All dirt, foreign contaminants, oil and laitance must be removed to assure a trouble free bond to the substrate. A test should be made to determine that the concrete is dry; this can be done by placing a 4'X4' plastic sheet on the substrate and taping down the edges. If after 24 hours, the substrate is still dry below the plastic sheet, then the substrate is dry enough to start coating.

PRODUCT MIXING

PLEASE ONLY PREPARE QUANTITY THAT MAY BE APPLIED DURING POT LIFE OF MIXTURE. MIX RATIO IS 1A:1B.

Lightly shake the A and B containers separately to place the solids content evenly in suspension. Pour component B and component A into the bucket using the proper mixing ratio of **1A:1B** by volume. **If you have a TINT PACK, mix in the tint pack with the A & B. 1 Pint (16oz) per 1.5-2 gallons of polyaspartic & 1 Quart (32oz) per 3 gallons of polyaspartic.** Mix both components for at least 3 minutes using a drill at low revolution (300 to 450 rpm) to reduce trapping of air. While mixing, scrape bottom and walls of the container at least once to ensure a homogenous mix. Only prepare the quantity that may be applied during pot life of mixture.

PRODUCT APPLICATION

The mixed material can be applied by brush or roller. However, the material can also be applied by a suitable serrated squeegee and then back rolled as long as the appropriate thickness recommendations are maintained. Maintain temperatures and relative humidity within the recommended ranges during the application and curing process. If concrete conditions or over aggressive mixing causes air entrapment, then an air release roller tool should be used prior to the coating tacking off to remove the air entrapped in the coating.

RECOATING OR TOPCOATING

If you opt to recoat or topcoat this product, you must first be sure that the coating has tacked off before recoating. PLEASE REFER TO THE REOCAT WINDOW STATED IN THE TDS. All previous coats should be deglossed to insure a trouble free bond prior to application of recoats or topcoats. Colder temperatures will require more cure time for the product before recoating or topcoating can commence. Many epoxy coatings as well as multiple coats of this product are compatible for use as a primer, build or topcoat coating. If using a product not sold by Armorpoxy please consult with your sales representative to ensure product compatibility.

CLEANING

Clean all tools and materials with the cleaner/thinner for epoxies. Wash hands and skin carefully with warm soapy water. Once product has hardened, it may only be removed through mechanical means.

FLOOR CLEANING

Caution! Some cleaners may affect the color of the floor installed. Test each cleaner in a small area, utilizing your cleaning technique. If no ill effects are noted, you can continue to clean with the product and process tested.

HEALTH AND SAFETY

In case of skin contact, wash with water and soap. In case of eye contact, immediately rinse with water for at least 15 minutes. Consult with a doctor. For respiratory problems, transport victim to fresh air. Remove contaminated clothes and clean before reuse. Components A and B contain toxic ingredients. Prolonged contact of this product with the skin is susceptible to provoke an irritation. Avoid eye contact. Contact with may cause serious burns. Avoid breathing vapors release from this product. This product is a strong sensitizer. Wear safety glasses and chemical resistant gloves. A breathing apparatus filtering organic vapors approved by the NIOSH/MSHA is recommended. Predict suitable ventilation.

NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY

We warrant that our products are manufactured to strict quality assurance specifications and that the information supplied by us is accurate to the best of our knowledge. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you shall make your own tests to determine the suitability of our product for your particular purpose. Any use or application other than recommended herein is the sole responsibility of the user. Listed physical properties are typical and should not be construed as specifications. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABILITY OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT. We shall have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Our products contain chemicals that may CAUSE SERIOUS PHYSICAL INJURY. BEFORE USING, READ THE MATERIAL SAFETY DATA SHEET AND FOLLOW ALL PRECAUTIONS TO PREVENT BODILY HARM.